

BARNIER® 3824

Polyethylene Single Sided Foam Tape

DESCRIPTION

Scapa 3824 is primarily a foam compression sealant. The product is white. The foam is predominantly closed celled. A rubber pressure sensitive adhesive is coated on one side, and the product has a polyethylene fixed liner on the other non-adhesive face. Scapa 3824 will act as a weatherseal and air/dust seal when compressed.

APPLICATIONS

- Allows the realization of moldings, chains of angle, bases and flat of frontage (for a thickness 5mm, to use the reference 3829)
- Rounding protection

PRODUCT BENEFITS

- Realization of moldings without briquettes. Fast realization of pronounced rounds
- Ease of application, time saving and low cost (replaces cleats)
- Adhesion on all substrates thanks to a very strong adhesive mass and whatever the temperature
- No interlayer, the roller stays alone
- Minimum 20% compression required to effect a weatherseal.
- Service temperature: -30°C to +80°C.
- Application temperature: +10°C to +40°C.

TECHNICAL PROPERTIES

Technical Property	Nominal Value	Unit	Test Method
10 Minute 180° Peel Adhesion	5	N/25mm	Scapa F9
Compression Deflection After 1 Minute	2.5	Ncm ⁻²	Scapa F4
Force To Compress By 30 %	3.0	Ncm ⁻²	Scapa F4
Shore Hardness {OO} Scale	55	"OO"	Scapa F16
Foam Density	33	Kg/m ³	-
Thermal Conductivity (k)	0.052	Wm ⁻¹ K ⁻¹	Lee's Disc

Note:

****This will be taken from the core product for the SAP Material Group****

STANDARD PRESENTATIONS

- Core: 76mm Scapa branded cardboard
- Dimension : 9mx19mm
- Packaging: 6

Note:

Other thicknesses - 4mm, 5mm, 6mm - are available against non stocked MOQ's. Please enquire.

RECOMMENDATIONS

Surfaces must be clean, dry, free from grease and dirt. Recommended cleaning agent is Propanol-2-ol, {IPA}. Please note manufacturer's safety instructions should be followed and customers are recommended to ensure compatibility of the solvent with their substrate. Ideal bonding substrates are those which are: clean, dry, flat, smooth, dust free & non-porous. Low temperatures may increase the risk of condensation, reducing the tack of the product. Life expectancy will vary with temperature and humidity. Product may be applied by hand direct from a roll applying even pressure. Customers are recommended to make their own assessment of our products under their own conditions, for their own requirements.